

Ø D_{RB}

API Grade Sinker Rods

Dimensions:

<u>Dimer</u>	<u>isions</u>	<u>.</u>								ŀ	Ø D _{PS}	
Nomin	al Size	Unite	DDD	DDC		114/6	DUR	LCD			\Longrightarrow	
Rod	Pin	Units	DKD	DPS	VV VV S	LVVS	DOB	LSK	LSP			
1"	3/4''	max. in (mm)	1.009 (25.63)	1.505 (38.23)	1.031 (26.19)	-	1.504 (38.20)	0.625 (15.88)	1.500 (38.10)	L _{SP}		
		min. in (mm)	0.982 (24.94)	1.490 (37.85)	0.969 (24.61)	1.250 (31.75)	1.378 (35.00)	0.594 (15.09)	1.437 (36.50)			T
1 1 /0"	7/8"	max. in (mm)	1.134 (28.80)	1.708 (43.38)	1.347 (34.21)	-	1.717 (43.61)	0.703 (17.86)	2.260 (57.40)	L _{ws}	W _{WS}	
1 1/8		min. in (mm)	1.107 (28.12)	1.693 (43.00)	1.253 (31.83)	1.250 (31.75)	1.568 (39.83)	0.672 (17.07)	1.630 (41.40)	(
*Dimensions according to API 11B.												
Sucker Rods Nominal Lengths: 25,				25, 30 ft (7	7.62 <i>,</i> 9.14 m)				-	Ø D _{UB}	

**Other lengths might be available upon request.

Steel Grades:

Different steel grades are available, depending on the type of load and the corrosion level in the wells. All these materials comply with API 11B.

Chemical Composition:

Typical chemical compositions (wt%) listed in the following table.

Grade	С	Mn	Si	S	Р	Cr	Ni	Мо	Others
DA Alloy	0.40-0.45	0.75-1.00	0.15-0.35	0.025 max	0.025 max	0.80-1.10	0.25 max	0.15-0.25	-
DS Special	0.29-0.37	0.70-0.95	0.15-0.35	0.025 max	0.025 max	0.80-1.10	1.65-2.00	0.20-0.30	V: 0.04-0.08
KDS Special	0.20-0.25	0.80-1.00	0.15-0.35	0.025 max	0.025 max	0.70-0.90	1.15-1.50	0.25-0.30	V: 0.03-0.07

Mechanical Properties:

Mechanical properties are listed in the following table.

Grade	Yield Strength (0.2% offset)	Ultimate Tensile Stress	Elongation (8")	Reduction of area	Hardness	
	min 95 kpsi	120 to 140 kpsi	10 % min	45% min	27 HRC	
DA Alloy	(min 655 MPa)	(827 to 965 MPa)	10 % 11111			
DS Special	min 100 kpsi	125 to 140 kpsi	10 % min	15% min	28 HRC	
DS Special	(min 689 MPa)	(862 to 965 MPa)	10 /8 ጠጠ	457611111		
KDS Special	min 85 kpsi	115 to 140 kpsi	10% min	15% min		
KDS Special	(min 586 MPa)	(793 to 965 MPa)	10/0 11111	4570 11111	25 TINC	

Performance Data: Maximum Pulling Force:

	Rod Outer Diameter		
Grade	1" pin 3/4"	1 1/8" pin 7/8"	
DA Alloy	55.5 klb (25.2 t)	71.8 klb (32.7 t)	
DS Special	58.4 klb (26.5 t)	75.6 klb (34.3 t)	
KDS Special	49.7 klb (22.6 t)	64.3 klb (29.2 t)	

To prevent tensile failures, the weight indicator pull on a "like new" condition rod string should not exceed 90% of the yield strength of the smallest diameter sucker rod, based on its known size and grade. Maximum pulling force values herein informed were calculated based on the 90% of the specified minimum yield strength at the smallest section of a given rod.

Beam Pumping: Maximum allowable tensile stress

It is recommended that the modified Goodman stress diagram or the simplified formula listed bellow are used in the determination of the allowable range of stress applied to a sucker rod.

$$S_a = \frac{UTS}{A} + B * S_{min} * SF$$

Applied tensions can be compared to the maximum allowable using the Goodman formula:

$$Goodman\% = \frac{S_{max} - S_{min}}{S_a - S_{min}} * 100$$

Where:

S_a = Maximum allowable stress (psi or Mpa)

S_{min} = Minimum calculated or measured stress (psi or Mpa)

S_{max} = Maximum calculated or measured stress (psi or Mpa)

UTS = Minimum ultimate tensile strength (psi or Mpa)

SF = Service factor. For corrosive environments a value of 0.9 is recommended

Coefficients A and B are listed on Table 1.

Table 1: Goodman coefficients.			
Grade	Α	В	
DA Alloy	4	0.5625	
DS Special	4	0.5625	
KDS Special	4	0.5625	

Progressive Cavity Pumping: Effective Stress

The effective rod stress in PCP applications can be calculated using the von Mises equation:

$$\sigma_e = \sqrt{\frac{(C_1 * L^2)}{\pi^2 * D^4} + \frac{C_2 * T^2}{\pi^2 * D^6}}$$

Where:

 σ_e = Effective stress (kpsi or Mpa)

L = Total axial load (lbf or N)

T = Total torque (lbf. ft or N. m)

D = Rod's body diameter (in or mm)

 C_1 = Constant (For imperial system= 1.6×10^{-5} . For international system= 16)

C₂ = Constant (For imperial system= 0.1106. For international system= 7.68x10⁸)

Color Code:

Rod's ends are painted according to the following table:

Grade	Color Code
DA Alloy	Yellow
DS Special	Orange
KDS Special	Orange

*Displayed colors are for guidance only.

Marking:



Grade	New Marking	Old Marking
DA Alloy	DA	D
DS Special	DS	DS
KDS Special	KDS	KD

Non Destructive Testing:

All raw material is carefully inspected using electromagnetic and/or ultrasonic methods to ensure the soundness of the final product.

Labeling:*

Tenaris

Metalmecánica S.A. Ruta 55 Km. 754,1 Villa Mercedes (San Luis)

Made in Argentina

BOX N°			QTY:
PRODUCT: S SAP CODE: SPECIFICATION:	SUCKER RODS		DATE:
ROD DIAM:	NET WEIGHT: (kg)		
END DIAM:		-	
GRADE:	1		
LENGTH: (ft)	1		
	-		
SALES ORDER:			PACKAGING TYPE:
DESTINATION:			THREAD PROTECTIO

Ordering Information:

When placing an order please attach the following information:

PDS:	SRSINRAPI
Product Family:	Sucker Rod (or Pony Rod)
Body Diameter:	1"
Pin Diameter:	3/4''
Grade:	KDS Special
Length:	25ft

*Image for reference only.

Tenaris has issued this document for general information only, and the information in this document is not intended to constitute professional or any other type of advice or recommendation and is provided on an "as is" basis. No warranty is given. Tenaris has not independently verified any information – if any- provided by the user in connection with, or for the purpose of, the information contained hereunder. The use of the information is at user's own risk and Tenaris does not assume any responsibility or liability of any kind for any loss, damage or injury resulting from, or in connection with any information contained hereunder or any use thereof. The information in this document is subject to change or modification without notice. Tenaris's products and services are subject to Tenaris's standard terms and conditions or otherwise to the terms resulting from the respective contracts of sale or services, as the case may be. Unless specifically agreed under such contract of sale or services, if Tenaris is required to provide any warranty or assume any liability in connection with the information contained here under, any such warranty or liability shall be subject to the execution of a separate written agreement between petitioner and Tenaris. For more complete information please contact a Tenaris's representative or visit our website at www.tenaris.com. All rights reserved. ©Tenaris 2025