

Sucker Rod String: Coupling

PDS: SRCPRAPISM

Short Name: C04

Effective Date: 23/12/2024 Previous Revision: 30/08/2024

Spray Metal API Polished Rod Coupling


Dimensions:

Full Size:

Nominal Size	Units	OD	Lc* (min)	Weight	
5/8"	in	1.500	4.000	1.17 lb	
5/6	mm	38.1	101.6	(0.530 kg)	
3/4"	in	1.625	4.000	1.4 lb	
3/4	mm	41.3	101.6	(0.633 kg)	
7/8"	in	1.811	4.000	1.72 lb	
	mm	46.0	101.6	(0.781 kg)	
1"	in	2.189	4.000	2.67 lb	
_	mm	55.6	101.6	(1.209 kg)	
1 1/8"	in	2.375	4.500	3.29 lb	
	mm	60.3	114.3	(1.494 kg)	

Slim Hole:

Nominal Size	Units	OD	Lc* (min)	Weight	
5/8"	in	1.252	4.000	0.66 lb	
5/6	mm	31.8	101.6	(0.300 kg)	
3/4"	in	1.500	4.000	1.05 lb	
3/4	mm	38.1	101.6	(0.478 kg)	
7/8"	in	1.626	4.000	1.14 lb	
	mm	41.3	101.6	(0.519 kg)	
1"	in	2.000	4.000	1.95 lb	
_ *	mm	50.8	101.6	(0.883 kg)	
1 1/8"	in	2.258	4.500	2.74 lb	
	mm	57.4	114.3	(1.244 kg)	



*Other lengths might be available.

Steel Grades:

Chemical Composition:

Typical chemical compositions (wt%) are listed in the following table.

Grade	С	Mn	Si	S	P	Cr	Ni	Мо	Others
TC carbon	0.26-	1.25-	0.15-	0.025	0.025	0.55	0.15	0.25	_
	0.35	1.55	0.35	max	max	max	max	max	-

Mechanical Properties:

Mechanical properties are listed in the following table.

Grade	Yield Strength	Ultimate Tensile Stress	Hardness
TC carbon	65 to 95 kpsi	95 to 125 kpsi	EC 63 HDA
	(448 to 655 MPa)	(655 to 861 MPa)	56-62 HRA

Coating:

API Spray Metal In accordance with API 11B

Thickness: 0.01-0.02 in (0.25-0.51 mm)

Max. Roughness (Ra): 40 μin (1.016 μm)
Hardness: 595 HV200 min

Chemical Composition:


Typical chemical compositions (wt%) listed in the following table.

Coating	С	Si	Р	S	Cr	В	Fe	Ni	Others
API Spray Metal	0.50-	3.50-	0.02	0.02	12.00-	2.5-	3.00 -	Remainder	Ti: 0.05 max Al: 0.05 max
Ari Spidy Wieldi	1.00	5.50	max	max	18.00	4.50	5.00		Zr: 0.05 max Co: 0.10 max

Other Technical Data:

All the dimensions comply with API 11B, except for the OD in the 1 1/8" SH.

Marking:



Old Grade Marking: T SM

Non Destructive Testing:

All raw material is carefully inspected using electromagnetic and/or ultrasonic methods to ensure the soundness of the final product.

Labeling:*



*Image for reference only

Ordering Information:

When placing an order please attach the following information:

PDS: SRCPRAPISM Coupling Type: Coupling

Nominal dimension: 1"

Size: Full Size
Grade: TC carbon

Coating technology: API Spray Metal

Tenaris has issued this document for general information only, and the information in this document is not intended to constitute professional or any other type of advice or recommendation and is provided on an "as is" basis. No warranty is given. Tenaris has not independently verified any information –if any- provided by the user in connection with, or for the purpose of, the information contained hereunder. The use of the information is at user's own risk and Tenaris does not assume any responsibility or liability of any kind for any loss, damage or injury resulting from, or in connection with any information contained hereunder or any use thereof. The information in this document is subject to change or modification without notice. Tenaris's products and services are subject to Tenaris's standard terms and conditions or otherwise to the terms resulting from the respective contracts of sale or services, as the case may be. Unless specifically agreed under such contract of sale or services, if Tenaris is required to provide any warranty or assume any liability in connection with the