


Chrome Plated Polished Rod with Wrench Flats

Product Description:

Polished Rods can be manufactured with two or four wrench flats depending on client's needs.

Dimensions:



Nominal Size		Units	Dpr	L3s	Lpf (min)	Lwf (min)	Wwf
Rod	Pin						
1 1/8"	5/8" PR	in	1.125	1.156	0.197	1.626	1.500
			+0.005				+0.031
		-0.010	-0.031				
		mm	28.6	29.4	5.0	41.3	38.1
+0.1	+0.8						
			-0.2				-0.8
1 1/8"	3/4" PR	in	1.125	1.406	0.197	1.626	1.500
			+0.005				+0.031
		-0.010	-0.031				
		mm	28.6	35.7	5.0	41.3	38.1
+0.1	+0.8						
			-0.2				-0.8
1 1/4"	7/8" PR	in	1.125	1.406	0.197	1.250	1.000
			+0.005				+0.031
		-0.010	-0.031				
		mm	28.6	35.7	5.0	31.8	25.4
+0.1	+0.8						
			-0.2				-0.8
1 1/2"	1" PR	in	1.500	1.780	0.197	1.500	1.311
			+0.005				+0.031
		-0.010	-0.031				
		mm	38.1	45.2	5.0	38.1	33.3
+0.1	+0.8						
			-0.2				-0.8
1 1/2"	1" PR - 3/4" PR	in	1.500	-	0.197	1.500	1.311
			+0.005				+0.031
		-0.010	-0.031				
		mm	38.1	-	5.0	38.1	33.3
+0.1	+0.8						
			-0.2				-0.8

Available Lengths* (Lpr): 8, 11, 16, 22, 26, 30, 36 ft ± 2"
(2.438, 3.353, 4.877, 6.706, 7.925, 9.144, 10.973 m ± 50.8 mm)

*Other lengths might be available upon request.

Steel Grades:

Chemical Composition:

Typical chemical compositions (wt%) are listed in the following table.

Grade	C	Mn	Si	S	P	Cr	Ni	Mo	Others
Carbon steel	0.43-0.50	0.60-0.90	-	0.050 max	0.040 max	-	-	-	-
Alloy steel	0.38-0.45	0.75-1.00	0.15-0.35	0.040 max	0.040 max	0.80-1.10	-	0.15-0.25	-

Mechanical Properties:


Mechanical properties are listed in the following table.

Grade	Ultimate Tensile Stress
Carbon steel	90 to 160 kpsi (620 to 1102 MPa)
Alloy steel	115 to 140 kpsi (793 to 964 MPa)

Coating: Chrome Plated

Double layer coated by electroplating process with anodic etching.


Roughness (Ra): 8-20 µin (0.203-0.508 µm)
Min thickness: 0.005 in (0.12 mm)
Hardness: 950-1150 HV



Coating Length	L1		L2	
Full length	0 "	0 mm	0 "	0 mm
1.5 ft free one end	18 " (± 2")	457.2 mm (± 50.8 mm)	0 "	0 mm

Other dimensions might be available upon request.

Marking:



Non Destructive Testing:

All raw material is carefully inspected using electromagnetic and/or ultrasonic methods to ensure the soundness of the final product.

Labeling:*

Tenaris
 Metalmecánica S.A.
 Ruta 55 Km. 754,1
 Villa Mercedes (San Luis)
 Made in Argentina

BOX N° 60000005	QTY:
PRODUCT: POLISHED ROD	DATE:
SPECIFICATION:	
ROD DIAM (in):	
GRADE:	
LENGTH (ft):	
NET WEIGHT (kg):	
SALES ORDER:	
DESTINATION:	

*Image for reference only

Ordering Information:

When placing an order please attach the following information:

PDS: SRPRCPWF
Body diameter: 1 1/2"
Pin diameter: 1" PR
Surface finish: Chrome Plated
Grade: Carbon steel
Length: 30 ft
Wrench flats: 2

Tenaris has issued this document for general information only, and the information in this document is not intended to constitute professional or any other type of advice or recommendation and is provided on an "as is" basis. No warranty is given. Tenaris has not independently verified any information -if any- provided by the user in connection with, or for the purpose of, the information contained hereunder. The use of the information is at user's own risk and Tenaris does not assume any responsibility or liability of any kind for any loss, damage or injury resulting from, or in connection with any information contained hereunder or any use thereof. The information in this document is subject to change or modification without notice. Tenaris's products and services are subject to Tenaris's standard terms and conditions or otherwise to the terms resulting from the respective contracts of sale or services, as the case may be. Unless specifically agreed under such contract of sale or services, if Tenaris is required to provide any warranty or assume any liability in connection with the information contained here under, any such warranty or liability shall be subject to the execution of a separate written agreement between petitioner and Tenaris. For more complete information please contact a Tenaris's representative or visit our website at www.tenaris.com. All rights reserved. ©Tenaris 2024