

Sucker Rod String: Sucker & Pony Rod

PDS: SRAPI Short Name: R01

Effective Date: 14/03/2025
Previous Revision: 23/12/2024

API Sucker & Pony Rod

Dimensions:

Available for both beam and progressive cavity pumping, Tenaris delivers sucker rods manufactured according to a rigorous quality assurance system that complies with ISO 9001 and API Q1 standards.

assarance system the	it complies t		OI and / ti	· Q± Staniat	45.				
Nominal Size	Units	DRB	DPS	wws	LWS	DUB	LSR	LSP	Ø D _{PS}
Rod	Ullits	DKB	DF3	VVVV3	LVV3		LJN	LSP	
5/8"	max. in (mm)	0.632 (16.05)	1.255 (31.88)	0.906 (23.01)	-	1.224 (31.08)	0.547 (13.90)	1.313 (33.34)	L _{SP}
	min. in (mm)	0.611 (15.52)	1.240 (31.62)	0.844 (21.44)	1.250 (31.75)	1.094 (27.78)	0.516 (13.11)	1.250 (31.75)	L _s
3/4"	max. in (mm)	0.758 (19.25)	1.505 (38.23)	1.031 (26.19)	-	1.411 (35.85)	0.625 (15.88)	1.500 (38.10)	W _{ws}
3,1	min. in (mm)	0.734 (18.64)	1.490 (37.85)	0.969 (24.61)	1.250 (31.75)	1.281 (32.54)	0.594 (15.09)	1.438 (36.51)	Lws
7/8"	max. in (mm)	0.883 (22.43)	1.630 (41.40)	1.031 (26.19)	-	1.505 (38.23)	0.703 (17.86)	1.688 (42.86)	
	min. in (mm)	0.859 (21.82)	1.615 (41.02)	0.969 (24.61)	1.250 (31.75)	1.375 (34.93)	0.672 (17.07)	1.625 (41.28)	Ø D _{UB}
1"	max. in (mm)	0.883 (25.63)	2.005 (50.93)	1.344 (34.14)	-	1.911 (48.55)	0.828 (21.04)	1.938 (49.21)	Ø D _{RB}
Ť	min. in (mm)	0.982 (24.94)	1.990 (50.55)	1.282 (32.56)	1.500 (38.10)	1.719 (43.66)	0.797 (20.24)	1.875 (47.63)	
1 1/8"	max. in (mm)	1.135 (28.83)	2.265 (57.53)	1.531 (38.89)	-	2.193 (55.69)	0.906 (23.02)	2.188 (55.56)	
	min. in (mm)	1.105 (28.07)	2.235 (56.77)	1.469 (37.31)	1.625 (41.28)	2.000 (50.50)	0.875 (22.23)	2.215 (53.98)	

Sucker Rods Nominal Lengths:

25, 30 ft (7.62, 9.14 m)

Pony Rods Nominal Lengths:

2, 4, 6, 8, 10, 12 ft (0.61, 1.22, 1.83, 2.44, 3.05, 3.66 m)

 * Other lengths might be available upon request.

Steel Grades:

Different steel grades are available, depending on the type of load and the corrosion level in the wells. All these materials comply with API 11B.

Grades C, K and DC carbon are only available under special request.

Chemical Composition:

Typical chemical compositions (wt%) listed in the following table.

Grade	С	Mn	Si	S	Р	Cr	Ni	Мо	Others
C Carbon	0.30-0.36	1.30-1.60	0.20-0.40	0.035 max	0.035 max	0.20 max	0.15 max	0.05 max	V: 0.15 max
K Alloy	0.18-0.25	0.70-0.90	0.15-0.35	0.035 max	0.035 max	0.30 max	1.65-2.00	0.20-0.30	-
DC Carbon	0.30-0.36	1.30-1.60	0.20-0.40	0.035 max	0.035 max	0.20 max	0.15 max	0.05 max	V: 0.15 max
DA Alloy	0.40-0.45	0.75-1.00	0.15-0.35	0.025 max	0.025 max	0.80-1.10	0.25 max	0.15-0.25	-
DS Special	0.29-0.37	0.70-0.95	0.15-0.35	0.025 max	0.025 max	0.80-1.10	1.65-2.00	0.20-0.30	V: 0.04-0.08
KDS Special	0.20-0.25	0.80-1.00	0.15-0.35	0.025 max	0.025 max	0.70-0.90	1.15-1.50	0.25-0.30	V: 0.03-0.07

Mechanical Properties:

Mechanical properties are listed in the following table.

Grade	Yield Strength (0.2% offset)	Ultimate Tensile Stress	Elongation (8")	Reduction of area	Hardness
C Carbon	min 60 kpsi	90 to 115 kpsi	13% min	40% min	
C Carbon	(min 414 MPa)	(621 to 793 MPa)	13% 111111	40% 111111	-
K Alloy	min 60 kpsi	90 to 115 kpsi	13% min	40% min	
K Alloy	(min 414 MPa)	(621 to 793 MPa)	13% 111111	40% MIN	-
DC Carbon	min 85 kpsi	115 to 140 kpsi	10% min	40% min	-
DC Carbon	(min 586 MPa)	(793 to 965 MPa)	10/6 111111	40/6 111111	
DA Alloy	min 95 kpsi	120 to 140 kpsi	10 % min	45% min	27 HRC
DA Alloy	(min 655 MPa)	(827 to 965 MPa)	10 /6 111111	45/6 111111	
DS Special	min 100 kpsi	125 to 140 kpsi	10 % min	45% min	28 HRC
	(min 689 MPa)	(862 to 965 MPa)	10 /6 111111	45/6 111111	
KDS Special	min 85 kpsi	115 to 140 kpsi	10% min	45% min	25 HRC
KD3 Special	(min 586 MPa)	(793 to 965 MPa)	10/0 111111	45/0 111111	

Performance Data:

Maximum Pulling Force:

	Rod Outer Diameter				
Grade	5/8''	3/4''	7/8''	1"	1 1/8"
C Carbon	15.8 klb	22.8 klb	31.3 klb	40.9 klb	51.8 klb
	(7.2 t)	(10.4 t)	(14.2 t)	(18.6 t)	(23.5 t)
K Alloy	15.8 klb	22.8 klb	31.3 klb	40.9 klb	51.8 klb
	(7.2 t)	(10.4 t)	(14.2 t)	(18.6 t)	(23.5 t)
DC Carbon	22.4 klb	32.3 klb	44.3 klb	57.8 klb	73.3 klb
	(10.2 t)	(14.7 t)	(20.1 t)	(26.3 t)	(33.3 t)
DA Alloy	25 klb	36.1 klb	49.5 klb	64.6 klb	81.9 klb
	(11.4 t)	(16.4 t)	(22.5 t)	(29.4 t)	(37.2 t)
DS Special	26.3 klb	38 klb	52.1 klb	68 klb	86.1 klb
	(12 t)	(17.3 t)	(23.7 t)	(30.9 t)	(39.2 t)
KDS Special	22.4 klb	32.3 klb	44.3 klb	57.8 klb	73.3 klb
	(10.2 t)	(14.7 t)	(20.1 t)	(26.3 t)	(33.3 t)

To prevent tensile failures, the weight indicator pull on a "like new" condition rod string should not exceed 90% of the yield strength of the smallest diameter sucker rod, based on its known size and grade. Maximum pulling force values herein informed were calculated based on the 90% of the specified minimum yield strength at the smallest section of a given rod.

Beam Pumping: Maximum allowable tensile stress

It is recommended that the modified Goodman stress diagram or the simplified formula listed bellow are used in the determination of the allowable range of stress applied to a sucker rod.

$$S_a = \frac{UTS}{A} + B * S_{min} * SF$$

Applied tensions can be compared to the maximum allowable using the Goodman formula:

$$Goodman\% = \frac{S_{max} - S_{min}}{S_a - S_{min}} * 100$$

Where:

S_a = Maximum allowable stress (psi or Mpa)

S_{min} = Minimum calculated or measured stress (psi or Mpa)

S_{max} = Maximum calculated or measured stress (psi or Mpa)

UTS = Minimum ultimate tensile strength (psi or Mpa)

SF = Service factor. For corrosive environments a value of 0.9 is recommended

Coefficients A and B are listed on Table 1.

T 11	4		
Iahla	1.	(-nodman	coefficients.
Iabic		Joournan	COCITICICITIES.

Grade	Α	В
C Carbon	4	0.5625
K Alloy	4	0.5625
DC Carbon	4	0.5625
DA Alloy	4	0.5625
DS Special	4	0.5625
KDS Special	4	0.5625

Progressive Cavity Pumping: Effective Stress

The effective rod stress in PCP applications can be calculated using the von Mises equation:

$$\sigma_e = \sqrt{\frac{(C_1 * L^2)}{\pi^2 * D^4} + \frac{C_2 * T^2}{\pi^2 * D^6}}$$

Where:

 σ_e = Effective stress (kpsi or Mpa)

L = Total axial load (lbf or N)

T = Total torque (lbf. ft or N. m)

D = Rod's body diameter (in or mm)

 C_1 = Constant (For imperial system= 1.6x10⁻⁵. For international system= 16)

 C_2 = Constant (For imperial system= 0.1106. For international system= 7.68x10⁸)

Color Code:

Rod's ends are painted according to the following table:


Grade	Color Code
C Carbon	White
K Alloy	Blue
DC Carbon	Brown
DA Alloy	Yellow
DS Special	Orange
KDS Special	Orange


*Displayed colors are for guidance only.

Non Destructive Testing:

All raw material is carefully inspected using electromagnetic and/or ultrasonic methods to ensure the soundness of the final product.

Marking:





Grade	New Marking	Old Marking
C Carbon	С	С
K Alloy	K	K
DC Carbon	DC	D
DA Alloy	DA	D
DS Special	DS	DS
KDS Special	KDS	KD



Metalmecánica S.A.

Ruta 55 Km. 754,1 Villa Mercedes (San Luis) Made in Argentina

BOX N°		QTY:
PRODUCT: SAP CODE: SPECIFICATION:	SUCKER RODS	DATE:
ROD DIAM:	NET WEIGHT: (kg)	
END DIAM:		
GRADE:		
LENGTH: (ft)		
		CONTRACTOR
SALES ORDER:		PACKAGING TYPE:
DESTINATION:	·	THREAD PROTECTIO

*Image for reference only.

Ordering Information:

When placing an order please attach the following

information:

PDS: SRAPI

Product Family: Sucker Rod (or Pony Rod)

Diameter: 1"

Grade: KDS Special

Length: 25 ft

Tenaris has issued this document for general information only, and the information in this document is not intended to constitute professional or any other type of advice or recommendation and is provided on an "as is" basis. No warranty is given. Tenaris has not independently verified any information –if any- provided by the user in connection with, or for the purpose of, the information contained hereunder. The use of the information is at user's own risk and Tenaris does not assume any responsibility or liability of any kind for any loss, damage or injury resulting from, or in connection with any information contained hereunder or any use thereof. The information in this document is subject to change or modification without notice. Tenaris's products and services are subject to Tenaris's standard terms and conditions or otherwise to the terms resulting from the respective contracts of sale or services, as the case may be. Unless specifically agreed under such contract of sale or services, if Tenaris is required to provide any warranty or assume any liability in connection with the information contained here under, any such warranty or liability shall be subject to the execution of a separate written agreement between petitioner and Tenaris. For more complete information please contact a Tenaris's representative or visit our website at www.tenaris.com. All rights reserved. ©Tenaris 2025