

Sucker Rod String: Coupling **PDS: SRCSRLS** Short Name: C33 Effective Date: 23/12/2024 Previous Revision: 31/01/2024

LaserShield[™] Sucker Rod Coupling

Through extensive R&D Tenaris introduced its new LaserShieldTM coating technology that enhance Sucker Rod Couplings performance.

Dimensions:

Full Size:

Nominal Size	Units	OD	Lc* (min)	Weight
5/8''	in	1.500	4.000	1.17 lb
	mm	38.1	101.6	(0.530 kg)
3/4''	in	1.625	4.000	1.4 lb
	mm	41.3	101.6	(0.633 kg)
7/8''	in	1.811	4.000	1.72 lb
	mm	46.0	101.6	(0.781 kg)
1"	in	2.189	4.000	2.67 lb
1	mm	55.6	101.6	(1.209 kg)
1 1/8"	in	2.375	4.500	3.29 lb
	mm	60.3	114.3	(1.494 kg)

Slim Hole:

Nominal Size	Units	OD	Lc* (min)	Weight
5/8''	in	1.252	4.000	0.66 lb
	mm	31.8	101.6	(0.300 kg)
3/4''	in	1.500	4.000	1.05 lb
	mm	38.1	101.6	(0.478 kg)
7/8''	in	1.626	4.000	1.14 lb
	mm	41.3	101.6	(0.519 kg)
11	in	2.000	4.000	1.95 lb
1	mm	50.8	101.6	(0.883 kg)
1 1/8"	in	2.258	4.500	2.74 lb
	mm	57.4	114.3	(1.244 kg)

Slim Hole Plus:

Nominal Size	Units	OD	Lc* (min)	Weight
7/8" SH Plus	in	1.705	4.000	1.48 lb
	mm	43.3	101.6	(0.670 kg)
1" SH Plus	in	2.090	4.000	2.31 lb
	mm	53.1	101.6	(1.050 kg)



Base Material Steel Grades:

LaserShield[™] couplings are manufactured using seamless hot rolled ultraclean alloyed steel pipes, calcium treated to modify inclusions to improve toughness. Pipes are heat treated to obtain the desired microstructure and mechanical properties.

Mechanical Properties:

Mechanical properties are listed in the following table.

Grade	Yield Strength	Ultimate Tensile Stress	Hardness	
High Strength	110 to 140 kpsi	125 to 155 kpsi		
	(758 to 965 MPa)	(862 to 1069 MPa)	52-30 HKC	

Coating Specification: LaserShield [™]

Coating Type: LW Material: Nickel Base Thickness: 0.007-0.02 in (0.20-0.51 mm) Max. Roughness (Ra): 15 μin (0.381 μm) Hardness: 780 a 1000 HV200

Application:

Due to its distinctive Tribocorrosion characteristics, LW coating reduces the wear on couplings and tubing in deviated wells, in addition its outstanding anti-corrosion properties make LW Coating the best option for medium and highly corrosive wells.

Marking:



Non Destructive Testing:

All raw material is carefully inspected using electromagnetic and/or ultrasonic methods to ensure the soundness of the final product.

Labeling:*

■ Tenaris		Metalmecánic: Ruta 55 Km. 1 Villa Mercedes (S Made in Arge	a S.A. 754,1 San Luis) ntina
BOX N°	600	00006	5
PRODUCT:			
SPECIFICATION:			
QTY:	DATE:		
DIAM 1: (in)	DIAM 2: (in)		
CLASS:	TYPE		
CLIENT:			Elevence a
SALES ORDER:			
DESTINATION:			NET WEIGHT:

Ordering Information:

When placing an order please attach the following information:

PDS:	SRCSRLS
Coupling Type:	Coupling
Nominal dimension:	1''
Size:	Full Size
Base Material Grade:	HS
Coating technology:	$LaserShield^{TM}$
Coating Type:	LW

*Image for reference only

Tenaris has issued this document for general information only, and the information in this document is not intended to constitute professional or any other type of advice or recommendation and is provided on an "as is" basis. No warranty is given. Tenaris has not independently verified any information –if any- provided by the user in connection with, or for the purpose of, the information contained hereunder. The use of the information is at user's own risk and Tenaris does not assume any responsibility or liability of any kind for any loss, damage or injury resulting from, or in connection with any information contained hereunder or any use thereof. The information in this document is subject to change or modification without notice. Tenaris's products and services are subject to Tenaris's standard terms and conditions or otherwise to the terms resulting from the respective contracts of sale or services, as the case may be. Unless specifically agreed under such contract of sale or services, if Tenaris is required to provide any warranty or assume any Iability in connection with the information contained here under, any such warranty or liability shall be subject to the execution of a separate written agreement between petitioner and Tenaris. For more complete information please contact a Tenaris's representative or visit our website at www.tenaris.com. All rights reserved. ©Tenaris 2024